

AKERUSTONE

SPECIFICATION

Providing & laying of factory blended concrete mix design in approved colour.

Installed on substrate prepared using special polymerised screed 45mm thick un-bonded using isolation membrane. Screed to be primed with 2 coats of epoxy resin prior to 5-10 mm overlay of akerustone – Compressive strength : after 7 days approx. 15N/mm², & after 28 days approx. 25N/mm² .

After curing for three days floors to be polished & sealed according to approved finish.